NASA Contractor Report 178113

FINITE ELEMENT ANALYSIS OF END NOTCH FLEXURE SPECIMEN

S. Mall and N. K. Kochhar

UNIVERSITY OF MISSOURI-ROLLA
ROLLA, MISSOURI

DEPARTMENT OF DEFENSE
PLASTICS TECHNICAL EVALUATION CENTER
ARRADCOM. DOVER. N. J.   07801

NASA

National Aeronautics and
Space Administration

Langley Research Center
Hampton, Virginia 23665

19951102 015

DTIC QUALITY INSPECTED 5

ABSTRACT

A finite element analysis of the end notch flexure specimen for mode II interlaminar fracture toughness measurement was conducted. The effect of friction between the crack faces and large deflection on the evaluation of G_{IIC} from this specimen were investigated. This analysis showed that the friction effect is negligible when crack length is greater than one-fourth of length of the specimen. Further, geometric nonlinear analysis is required to evaluate G_{IIC} when deflection is greater than the thickness of specimen.

1

INTRODUCTION

The delamination of laminated fiber reinforced composites is of current interest, particularly with regard to their durability and damage tolerance. It is the most commonly observed failure mode in composites. Fracture mechanics has been found to be a useful tool for understanding delamination [1]. Most of the work reported in this area has been concerned with the delamination in the opening mode, i.e. mode I. Delamination under shear sliding mode i.e. mode II and combined mode I-II situations are also the possible fracture modes of potentially greater significance in composite structures. Several studies on mixed-mode interlaminar fracture are also reported [1-4].

Recently attention has been given to mode II shear delamination [5-9]. Several investigators have used end notch flexure (ENF) specimen to measure shear mode strain energy release rate, G_{IIC}, for delamination growth [6-9]. This specimen is a beam with a crack (delamination) located on the neutral plane at one end and is subjected to the three-point bending. This specimen was initially utilized by Barrett and Foschi to measure Mode II critical-stress-intensity factor, K_{IIC}, for a strongly anisotropic fibrous material, wood [10]. Currently an ASTM task group is conducting a round robin test program using an end notch flexure specimen as a prelude to developing an ASTM standard for measurement of mode II interlaminar fracture toughness of composites. In this study, the end notch flexure specimen was analyzed using the finite element method for understanding its behavior and performance.

2

FINITE ELEMENT ANALYSIS

The end notch flexure specimen geometry is shown in Fig. 1.
Two geometries of the specimen were analyzed; (1) total length,
2L = 7.62 cm and (2) 2L = 10.16 cm. For both geometries, the
thickness (2h) of the specimen was taken equal to 0.30 cm which
is nominal thickness of a 24 ply composite panel. These dimensions
of L and h were selected since they were employed in experimental
works [6,9]. The width of specimen was 2.54 cm. Only one material
system was analyzed; unidirectional graphite/epoxy. The material
properties used in finite element analysis are presented in Table 1.

A two-dimensional finite element program called GAMNAS [11]
was used. A typical finite element mesh, shown in Fig. 2 consisted
of about 1000 isoparametric four-node elements and had about 2400
degrees of freedom. The element size in the vicinity of the crack
was 0.02 x 0.02 mm in order to evaluate accurately the strain energy
release rate G_{II}. This size was selected by previous experience [12]
as well as by conducting the convergence test on G_{II} calculation with
mesh refinement. The error in G_{II} obtained in the present study is
estimated to be less than ±2%. The strain energy release rate, G_{II},
in the analysis was computed using a virtual crack closure technique
[13]. Plane-strain condition was assumed in the finite element analysis.

The analysis indicated that mode II deformation is achieved at
the crack tip and that the accompanying mode I deformation causes
closure and overlapping of the opposite faces of the crack. This is
not possible physically. To prevent the overlapping of crack faces,
the nodal coupling technique, available with GAMNAS program [11],
was used. For this purpose, the multipoint constraint was applied
at corresponding nodes to have the same displacements normal to the

3

crack faces. This resulted in pure mode II condition, i.e. $G_I = 0$.
When the crack faces are pressed together as in this specimen,
friction effects will occur. The friction effects on G_{II} calculation
will be rather difficult to assess in the practical situation, however
a reasonable estimate of its role can be investigated with the finite
element analysis. The friction effect was modeled in the following
manner. The analysis was conducted intially with the frictionless
crack faces where displacements normal to the crack faces were
matched at corresponding nodes. The normal reactions at the crack
faces were obtained from this first step of calculation. The friction
forces at the nodes on the crack faces were calculated for the assumed
coefficient of friction. The finite element analysis of the specimen
was conducted with these computed friction forces applied at the crack
faces. This second step of analysis provided the new normal forces
at the crack faces and corresponding friction forces. The analysis
was repeated till the applied friction forces matched with the computed
normal reactions. This required about two or three iterations.

4

RESULTS AND DISCUSSIONS

Comparison Between Theoretical and FEM G_{II} Values

The measured compliance, c, versus crack length, a, relationship of a test specimen, in general, provides the most accurate evaluation of fracture toughness. However, it requires several measurements. On the other hand, fracture toughness can be measured from a single measurement of critical load if the necessary expression for G calculation is available. The experimental dc/da values were found to be subject to large errors due to small variation in compliance with crack length for small crack length values in the ENF specimen [7]. Therefore, the following expression for mode II strain energy release rate, G_{II} for this specimen was developed by Russell [7]:

$$G_{II} = \frac{9P^2a^2}{16b^2E_{11}h^3} \tag{1}$$

where P, a, b, h are defined in Fig. 1 and E_{11} is the Young's modulus in longitudinal direction. The G_{II}, as expressed above, is based on a linear beam theory where shear deformation is neglected and the curvature

$$\frac{1}{R} = \frac{d^2y/dx^2}{[1 + (dy/dx)^2]^{3/2}}$$

is approximated with $1/R \simeq d^2y/dx^2$. The G_{II} values obtained from FEM analysis and from Eq. (1) for both geometries of the specimens; (1) 2L = 7.62 cm and (2) 2L = 10.16 cm, are compared for the normalized crack length, a/L, ranging from 0.125 to 0.9. The normalized crack length commonly used for measurement of G_{IIC} with this specimen was 0.5 [6,7,9]. Figure 3 shows that G_{IIC} from a linear beam theory,

5

i.e. from Eq.(1), is within 8% and 6% of its counterpart from FEM analysis for a/L = 0.5 for specimens with 2L = 7.62 cm and 2L = 10.16 cm, respectively. Further, Fig. 3 shows that deviation between G_{II} from Eq.(1) and FEM analysis decreases with longer crack lengths and increases with shorter crack lengths. This comparison shows that the G_{IIC} should be evaluated from the end notch flexure specimen for $a/L \geq 0.5$ if Eq.(1) is used.

Effect of Overhang Length

The effect of overhang length beyond the support was also investigated with finite element analysis. Specimens with overhang lengths of 6.35, 12.7 and 25.4 mm on each side were analyzed. The G_{II} values obtained for these cases were within ±1% of each other. Thus, the overhang portion of this specimen has no effect in the evaluation of G_{IIC}.

Friction Effect

As mentioned previously, the friction was also modeled in FEM analysis. The most difficult task is to evaluate the actual coefficient of friction, μ, between two pressed crack faces of ENF specimen. This was beyond the scope of the present study. However, a simple experiment was performed to estimate the coefficient of friction between two unidirectional graphite/epoxy laminates. This experiment involved the measurement of the force to initiate sliding between the two laminates with a known compressive load. The coefficient of friction, μ, was found to be about 0.35. Therefore, the finite element analysis was conducted with the three values of $\mu = 0.1$, 0.3 and 0.5 to understand the role of friction in a qualitative manner. Results of this analysis are shown in Fig. 4. Several observations can be made from

this analysis. For crack length commonly used in experimental investigation, i.e. $a/L = 0.5$, the effect of friction is negligible for all practical purposes if μ is about 0.3. And, this effect is less in the ENF specimen with $2L = 10.16$ cm in comparison to specimen with $2L = 7.62$ cm. The friction effect shows a pronounced effect for shorter crack lengths and is negligible for longer crack lengths. This leads to an apparent conclusion that longer crack length should be employed for G_{IIC} evaluation, but this may cause the large deflection of specimen during testing and henceforth it may require the geometric nonlinear analysis as discussed later on.

The friction forces between the crack faces were primarily in the region above the support pin. Since it is always desirable to have the friction force as small as possible, it might, therefore, be preferable to use the shim. or rollers between the crack face just above the support pin to reduce the coefficient of friction. Barrett and Foschi [10] suggested the use of roller between crack faces for measurement of K_{IIC} of wood from this type of specimen. However, it may not be convenient in composite specimens due to their small thicknesses.

Geometric Nonlinear Analysis

To investigate the effect of finite rotation due to large deflection, the geometric nonlinear analysis of the ENF specimen was conducted with the GAMNAS finite element program [11]. This analysis was conducted without friction. Figure 5 shows the comparison of G_{II} obtained from linear and geometric nonlinear analysis for both geo-metries of specimens for crack length $a = 0.5L$. Linear and nonlinear solution

are in agreement with each other up to deflection, Δ, equal to the thickness of specimen, 2h. For larger deflection, i.e. $\Delta \geq$ 2h, the G_{II} would be overestimated from a linear analysis or Eq.(1). This overestimation depends on the deflection as shown in Fig. 5.

CONCLUDING REMARKS

A finite element analysis of the end notch flexure specimen for mode II interlaminar fracture toughness measurement was conducted. The effect of friction between the crack faces and large deflection on the evaluation of G_{IIC} from this specimen were investigated. Two geometries of the specimen, and one material system was studied. This study showed that this specimen should be preferably used for G_{IIC} measurement with crack length, $a \geq 0.5L$ and deflection, $\Delta \leq 2h$.

ACKNOWLEDGEMENT

REFERENCES

1. O'Brien, T.K., "Interlaminar Fracture of Composites", NASA TM 85768, June 1984.

2. Wilkins, D.J., Eisenmann, J.R., Camin, R.A., Margolis, W.S. and Benson, R.A., "Characterizing Delamination Growth in Graphite-Epoxy", Damage in Composite Materials: Basic Mechanisms, Accumulation, Tolerance, Characterization, ASTM STP 775, American Soc. for Testing and Materials, 1982, pp. 168-183.

3. Ramkumar, R.L. and Whitcomb, J.D., "Characterization of Mode I and Mixed-Mode Delamination Growth", Delamination and Debonding of Materials, ASTM, STP 876, American Society for Testing and Materials, Philadelphia, 1985, pp. 315-335.

4. Armanios, E.A., Rehfield, L.W., and Reddy, A.D., "Design Analysis and Testing for Mixed-Mode and Mode II Interlaminar Fracture of Composites" Composite Materials: Testing and Design (Seventh Conference), ASTM STP 893, American Society for Testing and Materials, Philadelphia, 1986, pp. 232-255.

5. Chatterjee, S.N., Pipes, R.B. and Blake, R.A., Jr., "Criticality of Disbonds in Laminated Composites", Effects of Defects in Composite Materials, ASTM, STP 836, American Society for Testing and Materials, Philadelphia, 1984, pp. 161-174.

6. Russell, A.J. and Street, K.N., "Moisture and Temperature Effects on the Mixed-Mode Delamination Fracture of Unidirectional Graphite Epoxy", Delamination and Debonding of Materials, ASTM, STP 876, American Society for Testing and Materials, Philadelphia, 1985, pp. 349-370.

7. Russell, A.J., "Factors Affecting the Interlaminar Fracture Energy of Graphite/Epoxy Laminates", Progress in Science and Engineering of Composites; Proceedings of ICCM-IV, Tokyo, 1982, pp. 279-286.

8. Giare, G.S., "Fracture Toughness of Unidirectional Fibre Reinforced Composites in Mode II", Engineering Fracture Mechanics, Vol. 20, No. 1, pp. 11-21, 1984.

9. Murri, G.B. and O'Brien, T.K., "Interlaminar G_{IIC} Evaluation of Toughened-Resin Matrix Composite Using the End-Notched Flexure Test", AIAA Paper No. 85-0647, Proceedings of the 26th AIAA/ASME/ASCE/AHS Structures, Structural Dynamics and Materials Conference, April 15-17, 1985, Orlando, FL.

10. Barrett, J.D. and Foschi, R.O., "Mode II Stress-Intensity Factors for Cracked Wood Beams", Engineering Fracture Mechanics, Vol. 9, pp. 371-378, 1977.

11. Whitcomb, J.D. and Dattaguru, B., "User's Manual for GAMNAS--
     Geometric and Material Nonlinear Analysis of Structures",
     NASA TM 85734, Jan. 1984.

12. Mall, S., Johnson, W.S., and Everett, R.A., Jr., "Cyclic Debonding
     of Adhesively Bonded Composites", Adhesive Joints: Their Formation,
     Characteristics, and Testing, K. L. Mittal, Ed; Plenum Press,
     New York, 1984, pp. 639-658.

13. Rybicki, E.F. and Kanninen, M.F., "A Finite Element Calculation of
     Stress Intensity Factors by a Modified Crack Closure Integral",
     Engineering Fracture Mechanics, Vol. 9, No. 4, 1977, pp. 931-938.

TABLE 1 - GRAPHITE/EPOXY MATERIAL PROPERTIES[a]

Modulus[b], GPa			Poisson's Ratio[b]	
E_{11}	E_{22}	G_{12}	ν_{12}	ν_{23}
131.0	13.0	6.4	0.34	0.35

a: $E_{33} = E_{22}$, $\nu_{13} = \nu_{12}$, $G_{13} = G_{12}$

b: The subscripts 1, 2 and 3 correspond to the longitudinal, transverse, and thickness directions, respectively, of a unidirectional ply.

Fig. 1. End Notch Flexure Specimen

Fig. 2. Finite Element Mesh (Y Coordinates are magnified 10X)

Fig. 3. Ratio of G_{II} from FEM analysis to G_{II} from Eq. (1) as a function of normalized crack length.

Fig. 4 (a). Ratio of G_{II} with $\mu = 0.0$ to G_{II} with $\mu = 0.1$ from FEM analysis as a function of normalized crack length.

Fig. 4 (b). Ratio of G_{II} with $\mu = 0.0$ to G_{II} with $\mu = 0.3$ from FEM analysis as a function of normalized crack length.

Fig. 4 (c). Ratio of G_{II} with $\mu = 0.0$ to G_{II} with $\mu = 0.5$ from FEM analysis as a function of normalized crack length.

Fig. 5. Ratio of G_{II} from nonlinear analysis to G_{II} from linear analysis as a function of normalized deflection.

Standard Bibliographic Page

1. Report No. NASA CR-178113	2. Government Accession No.	3. Recipient's Catalog No.
4. Title and Subtitle FINITE ELEMENT ANALYSIS OF END NOTCH FLEXURE SPECIMEN		5. Report Date May 1986
		6. Performing Organization Code
7. Author(s) S. Mall and N. K. Kochhar		8. Performing Organization Report No.
9. Performing Organization Name and Address University of Missouri-Rolla Department of Engineering Mechanics Rolla, MO 05401	M3943516	10. Work Unit No.
		11. Contract or Grant No. NAG1-425
12. Sponsoring Agency Name and Address National Aeronautics and Space Administration Washington, DC 20546		13. Type of Report and Period Covered Contractor Report
		14. Sponsoring Agency Code 534-06-23-03

15. Supplementary Notes

16. Abstract

A finite element analysis of the end notch flexure specimen for mode II inter-laminar fracture toughness measurement was conducted. The effect of friction between the crack faces and large deflection on the evaluation of G_{IIc} from this specimen were investigated. Results of this study are presented in this paper.

17. Key Words (Suggested by Authors(s)) Interlaminar fracture toughness Mode-II delamination End notch flexure specimen	18. Distribution Statement Unclassified-Unlimited Subject Category 24		
19. Security Classif.(of this report) Unclassified	20. Security Classif.(of this page) Unclassified	21. No. of Pages 20	22. Price A02

NASA Langley Form 63 (June 1985)